Hypertherm[®]

HyPerformance® Plasma HPR260XD®

The HPR260XD delivers superior HyPerformance cutting across a broad range of application needs, from very thin to heavier thicknesses.

Mild steel cut capacity				
Dross free*	32 mm			
Production pierce	38 mm			
Maximum cutting capacity	64 mm			
Stainless steel cut capacity				
Production pierce	32 mm			
Maximum cutting capacity	50 mm			
Aluminum cut capacity				
Production pierce	25 mm			
Maximum cutting capacity	50 mm			

^{*} Feature and material type can influence dross free performance.

Superior cut quality and consistency

HyPerformance Plasma cuts fine-feature parts with superior quality and consistency, eliminating the cost of secondary operations.

- HyDefinition® technology aligns and focuses the plasma arc for more powerful precision cutting up to 64 mm on mild steel.
- New HDi™ technology delivers HyDefinition cut quality on thin stainless steel from 3 to 6 mm.
- Patented system technologies deliver more consistent cut quality over a longer period of time than other systems available on the market.

Maximized productivity

HyPerformance Plasma combines fast cutting speeds, rapid process cycling, quick changeovers and high reliability to maximize productivity.

Minimized operating cost

HyPerformance Plasma lowers operating cost and improves profitability.


 LongLife® technology significantly increases consumable life and enables consistent HyDefinition cut quality over the longest period of time.

Unmatched reliability

Extensive testing, backed by more than four decades of experience, guarantees the Hypertherm quality you can count on.



Cut quality over life (260 A)



Superior cut quality on mild steel and stainless steel



Specifications

оросписации					
Input voltages (3-PH) and currents	VAC 200/208 220 240 380 400 415 440 480 600	Hz 50/60 50/60 60 50/60 50/60 50/60 60 60	Amps 149/144 136 124 84 75 75 68 62 50		
Output voltage	175 VDC				
Output current	260 A				
Duty cycle	100% at 40°C at 45,5 kW				
Power factor	0,98 @ 45,5 kW output				
Maximum OCV	311 VDC				
Dimensions	260 A 100% at 40°C at 45,5 kW 0,98 @ 45,5 kW output				
Weight with torch	567 kg				
Gas supply Plasma gas Shield gas Gas pressure	O ₂ , N ₂ , F5*, H35**, Air, Ar N ₂ , O ₂ , Air, Ar 8,3 bar Manual gas console 8 bar Automatic gas console				

^{*} $F5 = 5\% H, 95\% N_2$













Cut with confidence

- Hypertherm is ISO 9001: 2000 registered.
- Hypertherm's full-system warranty provides complete coverage for one year on the torch and leads and two years on all other system components.
- Hypertherm's plasma power supplies are engineered to deliver industry leading energy efficiency and productivity with power efficiency ratings of 90% or greater and power factors up to 0,98. Extreme energy efficiency, long consumable life, and lean manufacturing lead to the use of fewer natural resources and a reduced environmental impact.

Operating data

	Current	Thickness	Approximate cutting speed
Material	(amps)	(mm)	(mm/min)
Mild steel O ₂ plasma O ₂ shield	30	0,5 3 6	5355 1160 665
0_2 plasma Air shield	80 [†]	3 12 20	6145 1410 545
0_2 plasma Air shield	130†	6 10 25	4035 2680 550
$\mathbf{0_2}$ plasma Air shield	200†	10 20 32	3460 1575 750
$\mathbf{0_2}$ plasma Air shield	260 [†]	12 20 32	3850 2170 1135
Stainless steel F5 plasma N ₂ shield	60	3 4 5 6	2770 2250 1955 1635
${ m H35}$ and ${ m N_2}$ plasma* ${ m N_2}$ shield	130 ⁺	6 12 20	1835 875 305
${ m H35}$ and ${ m N_2}$ plasma* ${ m N_2}$ shield	200	8 12 20	2000 1800 1000
H35 plasma N₂ shield	260 ⁺	10 12 20	2030 1710 1085
$H35$ and N_2 plasma* N_2 shield	260†	10 12 20	2190 1790 1320
Aluminum H35 and N ₂ plasma* N ₂ shield	130	6 12 20	2215 1455 815
$H35$ and N_2 plasma* N_2 shield	200	8 12 20	4350 3650 1050
H35 plasma N ₂ shield	260	12 20 32	4290 1940 940

[†]Consumables support up to 45° bevel capability.

The operating data chart does not list all processes available for the HPR260XD.

Please contact Hypertherm for more information.

One of Hypertherm's long-standing core values is a focus on minimizing our impact on the environment. Doing so is critical to our, and our customers', success. We are always striving to become better environmental stewards; it is a process we care deeply about.



Hypertherm, HyPerformance, HPR, HyDefinition, HDi and LongLife are trademarks of Hypertherm Inc. and may be registered in the United States and/or other countries. All other trademarks are the properties of their respective owners.

© 8/2016 Hypertherm Inc. Revision 6









^{**} H35 = 35% H, 65% Ar

^{*} H35 and N_2 mixed plasma gas requires the use of an autogas console.